

1

TIPS TO INSTALL VICENZA STONE

Giallo Dorato
Grigio Argento
Bianco Avorio
Pietra del Mare
Grigio Alpi

FRANCESCO GRASSI Architect

General index:

- 1) Introduction**
- 2) Preliminary indications to installation**
- 3) Installation of tiles on floors and walls with adhesives (glue)**
- 4) Other types of shutter funds**
- 5) Adhesives for installation**
- 6) Practical tips for cutting and grouting**
- 7) Anchors for exterior cladding**
- 8) Grouting**
- 9) On site honing**
- 10) Water-oil repellent sealant**

1) Introduction

Stones and marbles are natural products and thus they may differ in color (mild shades of color, slight grain difference, slight variations in hue, more or less intense presence of fossils, etc.) giving value and uniqueness to the product. The present guide gives useful indications to prevent mistakes and gives suggestions following "the best rules of art", but only with the help and cooperation of expert installers you can create a work that values and celebrates the beauty of natural materials that are going to be installed. Our materials are suitable for many different uses. Among these, the most common are floors, walls cladding, architectural elements and structural jobs, like doors and window frames, skirtings, stairs, columns, balustrades, kitchens and bathrooms elements.

Here You find techniques and tips to install flooring and cladding tiles while for structural elements (like windows and doors surround, windows, sills, railings, etc.) the ways of fixing may be different and must be chosen considering the construction site, the workers, the type of product together with a professional installers.

We will give You anyway some info, in case of specific project please contact our technical department for further suggestions.

Vicenza Stone can be produced with "only sawn "finishing" (raw, blade cut sawn or calibrated), "honed", "bushhammered", "brushed" or "sand blasted". For "only sawn" surface, "bushhammered surface" and "sandblasted" surface the calibration is not normally done, and tolerances on the thickness of the tiles shall be $\pm 1 / 2$ mm.

Only on request we can calibrate the thickness, doing this calibration on the back side of the tile, but this is an extra working and is not normally required, thus is not normally included in the price.

Instead, for the following finishing: "sawn and calibrated", "honed", "brushed", tiles of standard sizes are calibrated as following:

- 1.8 cm (for elements of nominal thickness of 2 cm)
- and 1.3 cm for those of nominal thickness 1.5 cm.

Normally with calibration approx 2 mm are removed, so a nominal tile 3 cm honed will be 2.8 cm thickness. The calibration is a necessary operation to lay on screed (especially if tiles are installed with small joints) and for glued claddings.

On all finishing and for most uses we highly recommend, after installation, to apply a water-oil repellent sealant to prevent atmospheric pollution absorption, and also to avoid staining of the stone with the substances normally used in houses such as coffee, oil, wine and other substances that may affect the natural color of the material. So we recommend also our "guidelines to sealing and maintaining the stone" to ensure that a good supply and an accurate installation are undermined by the lack of protection and maintenance.

The installation of our materials can be made "fresh", laying the tiles directly on the just made screed, so "fresh" (made with cement mortar) or by the use of pre-mixed adhesives.

The first method was the traditional technique and once it was the most widely used: it consisted in the setting of tiles on the fresh screed, after spreading the surface with some cement, then lightly beating the tiles to make them adhere to the substrate. This technique is still in use, there are no contraindications for Vicenza stone, but we recommend using the other way, thus installing by adhesives rather than on fresh cement mortar, since the chemical compositions of the cements and of water are not the same all over the world, and sometimes, the chemicals inside it can cause unexpected chemical reactions (efflorescence, flowering corrosion, etc.) because of a reaction with the minerals inside the stone.

This general consideration applies to the laying of floors and thin pieces in general (being less dimensional stable and being more subject to possible staining from the background) .

The installation of building materials such as stairs, window sills and thresholds can be done on fresh mortar or so-called "bastard" grout (binder mixed with cement and hydraulic lime).

In this discussion we will therefore analyze the floor and cladding installation with adhesives but please refer to the literature and indications of manufacturers of brackets for the realization of "ventilated walls."

2) Preliminary indications for installation

Vicenza Stone is a natural material produced by millions of years of organic sediment and may present slight variations in color and texture , so it is recommended to go over the material before installation (in case of a flooring it is a good idea to check tiles in all crates),to lay a few pieces, see any veins or presence of fossils to find the right combination of colors to lay and by combining any changes in the grain or texture.

During installation You can comply with the laying towards the sedimentation (and fossil) or against them by placing tiles side by side in the opposite way.

We suggest to wet the surface of the stone (when laying raw materials) to see the actual shades of the material. We also suggest to dry install a few square meters of flooring or cladding to get a first effect of finished work (with tiles arranged in the expected direction and with the right dimensions of the joints). So You can verify the compliance to the project and expectations.

We suggest the installer should work with light gloves to allow him to appreciate the finishing of the stone surface , to avoid installing tiles with the back part up.

Please unload of pallets from the means of transport only with forklifts or cranes, with appropriate forks. Avoid the use of belts. We also suggest you to take the utmost care in unpacking the tiles to avoid unpleasant chipping and scratches on them.

3) Installation of floor and wall tiles with pre-mixed adhesive (glue)

Before installing:

The installer , to ensure the success of the work , needs to perform , before installing , the necessary tests to determine the degree of flatness, stability and consistency of the fund and the residual moisture content of the substrate.

The Substrate: screeds and plasters :

Substrates must be flat (for floor screeds) or level (for plastered walls coatings), stable from a dimensional point of view, consistent and free of loose parts, perfectly clean and free from shavings, crusts of cement, dust, oils, waxes, or efflorescence or other release agent.

The substrate is ready for the installation when the moisture content has reached values below 2.5-3%, for cement surfaces, and 0.5 - 1% for the screed or the plasters. It is a good practice to lay the stone when substrates are mature, i.e. have at least 28 days for screeds made from sand and cement.

For the floors that needs to be put into operation quickly, you can use pre-mixed screeds that include hardening and rapid hydration binders that, containing a low percentage of residual humidity (about 2%) and for the absence of shrinkage, allow the installation of marble after a few hours.

4) Other types of substrate

Gypsum plaster boards:

Vicenza stone can be installed on gypsum plaster board but they should be left with a natural surface, without smoothing, and they must have a proper thickness (at least 10-13 mm). The panels must be rigidly fixed by mechanical anchoring. All connections between the panels that are subject to movement are considered joints, and therefore must also be observed and confirmed in the stone cladding.

Please apply any primer before the installation of the stone. Furthermore, as in the shower box, to prevent the moisture that can pass by the stone and deteriorate the plasterboard, you have to apply an insulating mortar like MAPEI MAPELASTIC before the installation of the stone.

Please apply primer (like PRIMER G, Mapei) or insulating water-repellent or waterproof membranes prior to gluing the stone slabs when the stone will be under continuous action of water (for example in showers) to prevent the moisture, that will eventually pass through the cladding, could ruin the plasterboard support.

Old ceramic floors or marble floor :

It is possible to install Vicenza stone on old floor but these need to be stable, adherent to the substrate and without pre-existing cracks.

Before laying the new floor, the old floor should be scraped off and / or washed with acid or alkali to remove residual mortar, separating substances, oils, fats or waxes.

Metal sheet :

You can install Pietra di Vicenza on metal sheets but before doing that you must remove all traces of old paint, of elements that might separate, of fatty or oily patina and any rust, this with specific cleaning agents, with solvents or abrasive machines.

The gluing of stone elements on this type of support might require special glues (not cement based but resin based), or appropriate adhesives based on epoxy or acrylic resins.

Remember that the coefficient of thermal expansion of the metal is much higher than natural stone so it will be important to create common expansion joints and comply with the laying of the structural joints.

5) Adhesives for installation

The choice of adhesive

To choose the adhesive (glues, cements, fillers and detergents) it is necessary to ask the technical office of the adhesives' suppliers, providing clear information about the type of materials that should be installed, where will the material be installed, special climate requirement and weather conditions (very hot or very cold temperatures, frequency of rainfalls, humidity rates, etc.) to be encouraged and backed up by the same companies that can help you choose the best solutions, to address and prevent any problem that can arise.

Please find here some general consideration. But remember that similar adhesives, with same technical characteristics, can be also employed.

To install floors and internal cladding You can employ white cement based glues like Mapei "Keraflex white". In the case of interior floors and walls that are subject to heavy load or for floors and walls in need of rapid installation you can use Mapei "Granirapid" glue. Please refer to the instruction of the producer to understand the right installation way. In case of installation of stone with large format you should use KERAFLEX MAXI or GRANIRAPID to prevent bending of the material.

To install external cladding panels, please use a an adhesive with high deformability characteristics , like Mapei "Ultraflex 2 mono "or similar products. You need anyway to perform preliminary tests to verify the accuracy of the result and the conformity of the product to the required performance both for wall and floor. Of course also installators' experience play a key role in the process.

6) Practical tips for cutting and grouting

Cut the stone preferably with electric diamond disc circular saw , with water cooling or dry. You can also do dry cuts with cutting blade (diamond or normal) flexible but the cut won't be so smooth and straight. So if the cut remains seeble , we suggest the use of a circular saw .

To clad angles we don't suggest 45° cut because of chipping that will come out. However, if the project involves the 45 ° cuts , we suggest these elements to be made in a factory. When performing the 45° cut, we normally leave approx 2 mm left horizontally untouched , after that the real 45° cut is made.

During installation , You have to install the two pieces and fill the space between the two edges, then rectify it. It is still better to make the "side working " honed instead of a 45° cut . To drill holes on the stone , we suggest to use rotational drills (using normal heads for concrete). To make big holes big , perform a preliminary guiding hole of smaller diameter.

Please put particular attention in performing "through" holes, to prevent large chipping on the back of the plate. Vicenza Stone usually has a pretty rough finish (sanded, brushed or honed , never shining) thus You may easily fix eventual "chipping", breakage or scratches that might happen on site.

Fillings can be made in two ways:

A) **Plastering with white cement and stone dust**

These grouts are recommended for small thicknesses or to seal small holes or cracks in the surface of the stone: to perform the grouting You need to make a mortar composed of stone dust (the same color of the stone) and white cement in the proportions : Powder 2.5 part ; cement 1 part . This mixture should be wet with water to obtain the desired consistency (to achieve filling of small holes or slits it can be also fluid while to repaire nicks and edges, even vertically, it must be more " pasty"). You must wet in advance the part that has to be plastered on the stone (to avoid that the stone absorbs all the water in the mix) then you can do the grouting.

After applying the grout , please remove the excess material with a sponge or fine sandpaper. The fillings done in this way can take several hours to harden , and the end consistency is only reached after several days. If you have the necessary to accelerate the installation and if You want to avoid the dough retirement , You need to use acrylic latices or rubber based to improve the adhesion of the mortar grouting to the bottom.

B) **Mastix Fill and repairing**

These grouts are recommended to perform larger size bonding and to glue broken pieces (for example due to accidental impacts) . The bonding must be done with a dough-based mastic like Tenax straw (or other acrylic or polyester base mastics of other producer) together with the stone powder . It must be hard enough to keep the workability of the product while installing it .

This paste is spread on the two parts of the detached stone , and then the stones are leaned one against the other , exercising a pressure for a few minutes until the glue has set. After that the material can be sanded or hand sanded or honed using a flexible abrasives. Please note most of the adhesives are sensitive to ultraviolet rays, and some products glued fear frost, so it is advisable to check whether the glued product is fit for its use.

It is important to do a test before performing all fillings . Please note that cement based grouting is easier to be done, and also to be taken away in case of need, while mastic fillings and bondings are more rigid and usually should be carried out only by trained personnel.

7) Anchors for exterior cladding

In the case of external claddings, slabs must be fixed with stainless steel brackets . These have to be fixed to the wall with chemical glue , and to the stone on the above side, producing thus a safe anchorage that will last in time.

The brackets can be purchased directly from brackets manufacturers (for examples, product Fischer F4 / A or similar) or they can be produced on site with threaded rods of stainless steel or improved adhesion rods stainless steel AISI 304. The rods or bars will have to be of small diameter , approx 3 mm, in order to be folded and shaped to L.

8) Grouting

Joints can be done in different ways depending on whether you want the joint to have a very similar color to the stone, or very different, marking it and visually isolating the individual stone elements that make up the floor or cladding. Both solutions can be realized using mixtures of cement and stone powder or using ready pre-mixes products. The use of cement is the traditional way of doing joints: You have to mix fine stone powder (possibly sieved before use) with white cement in the proportions:

1: 2.5 (1 part cement to 2.5 parts of powder)

You can add acrylic latex to the mixture to prevent shrinkage. More instruction in the section "Plastering with white cement and stone dust" in this same file. Groutings made this way are rigid and not particularly suited for exterior cladding constructions , but it is used mostly for interior applications.

The second type of grouting involves the use of appropriate premixed products (already available on the market in different colors like Mapei cement based grouts Keracolor FF or similar). These products are specially designed according to the dimensions of the joints and according to the required grouting color.

For the fillings of external cladding or where expansion joints are needed, please use high elastic product, for example Mapei Mapesil LM or similar.

Please note that very colourful grouting and filling might be absorbed by the stone, damaging it, so

- Clean debris before grouting hardens and before it enters into the stone, so You avoid to remove it by abrasion with sandpaper later . If you need to do a grouting with bright colors we suggest to pre treat with water-oil repellent the stone, to protect the surface when grouting.

- Carefully protect the floor in the finishing phase of the local to avoid bringing the dirt and mortar grouting of the tiles on the finished floor .

To ensure the integrity of the cladding , splitting joints are required. Normally they have a width of approx 10 mm, they will allow the cladding to expand and absorb the effects of eventual flexion. These joints are done every 4-5 m inside and every 3-4 m outside (at least every 25 square meters

indoors and 16 square meters outdoors). The joints must be sealed with adhesive or elastic using special PVC flexible joints.

We suggest at least a 1 / 2 mm joints. between the tiles to allow the grout to go deep and adhere well. When selecting the shade of the grout please give a try by mixing the grout with a little water, then let it dry and then check the tone of the dried product. In case of changes, we recommend mixing the grout colors with different quantity of coloring and make several samples with different proportions. Once the required colour is reached, we recommend to mix the stucco dry, and mix with water only part of the mix, then fill the floor. After a few hours after grouting , the floor or wall should be washed with a sponge and when the surface of the stone is dry but filling in spaces is still wet, you will have to re-apply the putty to close every pore and any edges or imperfections of the edge of the tiles, that remaining in evidence with the sponge Then proceed by removing the excess grout with a broom and a perfectly dry and clean cloth.

When installing tiles whose surface is already finished (honed finish, brushed, etc.) the grout is given only to the joint between the tiles. Remove with wet sponge the surplus of stucco to prevent the mortar to be absorbed by the stone and creates stains. In the event that you are installing only sawn tiles on the floor or sawn calibrated , grouting will be made to all the floor (so both in the joints between the tiles and over the surface of the tile) in order to saturate any small minute excoriations of the stone. You need to wait at least 15 -20 days after installation before honing on site the surface .

9) On site honing

The on site honing is recommended in the works that require a final result of perfectly coplanar paving . Here joints almost disappear. This way is also recommended for elaborate designs and with different types of materials. The onsite honing produces a very aesthetical refined and smooth. flooring . Before performing the honing, You must wait for the glue fixing to be mature (for elements installed with Keraflex and grouted with Keracolor you must wait at least 15-20 days after the end of the laying and grouting).The honing work involves the complete wetting of the floor and honing is done with heavy machines (usually operating with electricity 380 volts, normally You need a power of 5 Kw, but You can also use smaller machines , electricity at 220 volts with 2 kW of power). The honing also involves the formation of sludge (dust stone, and water) that are to be readily removed and confined to avoid excessive wetting of the stone walls and floor .

The honing work is recommended for construction of medium-large size (where the stone paving extends for at least 80-100 m²), so it is not recommended for small jobs (20 or 30 square meters of stone). The honing increase the time of completing the flooring , as after completing it You will need at least 15/20 days before You can put any kind of water-oil repellent sealant (You need the floor to be fully dry)

10) Water – oil repellent sealant

After the installation operations you need to apply a water-oil repellent treatment on clean and dry stone. To choose the most suitable type of product You can refer to the appropriate tab for the treatment , see "Guide for treatment".